

CHEMICAL RESISTANCE

GUIDE

The following guide has been prepared to assist in the selection of the correct hose for an application.

A hose's resistance to the effects of a chemical depends not only upon the particular chemical, but also on other factors such as service temperature, length of exposure, pressure and conditions which may be beyond our control.

Therefore the recommendations are made without guarantee or warranty.

As we use plasticisers to give our hoses their flexibility, some solvents will extract these plasticisers thus making the hose become hard. Some oils & petrols will also extract the plasticiser, but in some cases the hose will retain its flexibility as long as it is not allowed to dry out. The oil actually replaces the role of the plasticiser and the hose will remain flexible whilst the oil or petrol remains in the hose and not allowed to evaporate.

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC	LLDPE	EVA	Material Handled						PVC	LLDPE	EVA	
	Temperature (°C)						Temperature (°C)						
	20	65	20	65	20	65		20	65	20	65	20	65
Acetaldehyde	U	U	G	L	G	U	Aniline Hydrochloride	U	U	U	U	U	U
Acetate Solvents- Pure	U	U	E	G	L	U	Animal Oils	L	U	L	U	L	U
Acetic Acid - Glacial	L	U	L	U	U	U	Anthraquinone	E	E	E	E	E	-
Acetic Acid - 0-10%	E	G	E	G	E	E	Anthraquinonesulfonic Acid	E	E	E	E	E	-
Acetic Acid - 10-20%	G	L	E	G	E	G	Anitomy Trichloride	E	E	E	E	E	-
Acetic Acid 20-30 Pct	G	L	E	G	E	L	Apple (Sauce or Juice)	E	E	E	E	-	-
Acetic Acid 30-60%	G	L	G	L	L	U	Aqua Regia	L	U	U	U	U	U
Acetic Acid 80%	L	L	U	U	L	U	Aromatic Hydrocarbons	U	U	-	-	-	-
Acetic Acid Vapors	G	G	G	L	G	L	Arsenic Acid 80%	E	G	E	G	G	-
Acetic Anhydride	U	U	U	U	L	L	Arylsulfonic Acid	L	U	-	-	-	-
Acetone	U	U	E	G	L	U	Asphalt	L	U	L	U	U	U
Acetylene	C	C	U	U	U	U	Barium Carbonate	E	E	E	E	E	-
Acrylonitrile	L	U	-	-	-	-	Barium Chloride	E	E	E	E	E	-
Adipic Acid	G	L	E	G	E	G	Barium Hydroxide	E	E	E	E	E	-
Allyl Alcohol 96%	U	U	E	G	E	G	Barium Sulfate	E	E	E	E	E	-
Allyl Chloride	U	U	G	L	L	U	Barium Sulfide	E	E	E	E	E	-
Alum	E	E	E	E	E	G	Beer	E	L	E	L	-	-
Aluminum Chloride	E	E	G	G	G	C	Beet-Sugar Liquor	E	E	E	E	E	-
Aluminum Fluoride	G	G	G	G	G	L	Benzaldehyde	U	U	E	G	L	U
Aluminium Hydroxide	E	E	G	G	G	G	Benzene	U	U	E	L	U	U
Aluminium Nitrate	E	E	E	E	E	-	Benzoic Acid	G	L	G	G	G	-
Aluminium Oxychloride	E	E	G	G	G	-	Benzol	U	U	U	U	U	U
Aluminium Sulfate	E	E	E	E	E	-	Bismuth Carbonate	E	E	E	E	E	-
Ammonia - Aqueous	L	U	E	G	E	-	Black Liquor (Paper Ind)	E	E	E	E	E	-
Ammonia - Dry Gas	L	U	E	G	E	-	Bleach 12.5% Active Cl.	G	L	G	L	G	-
Ammonia - Liquid	U	U	E	L	E	U	Borax	E	E	E	E	E	-
Ammonium Carbonate	E	E	E	E	E	-	Boric Acid	E	E	E	E	E	-
Ammonium Chloride	E	E	E	E	E	-	Boron Trifluoride	E	E	E	E	E	-
Ammonium Fluoride 25%	U	U	G	G	G	-	Brake Fluid	U	U	-	-	-	-
Ammonium Hydroxide 28%	L	U	E	E	E	E	Brine	E	E	E	E	E	-
Ammonium Metaphosphate	E	E	G	G	E	E	Bromic Acid	E	L	G	G	G	-
Ammonium Nitrate	E	E	E	E	E	-	Bromine - Liquid	U	U	U	U	U	U
Ammonium Persulfate	E	E	E	E	E	-	Bromine - Water	U	U	U	U	U	U
Ammonium Phosphate	G	G	E	G	E	-	Butadiene	L	U	U	U	U	U
Ammonium Phosphate - Neutral	E	E	E	G	E	-	Butane	C	C	U	U	U	U
							Butanol - Primary	U	U	E	G	G	-
Ammonium Sulfate	E	E	E	E	E	-	Butanol - Secondary	U	U	E	G	G	-
Ammonium Sulfide	E	E	E	E	E	-	Butter	L	L	L	L	-	-
Ammonium Thiocyanate	E	E	E	E	E	-	Butyl Acetate	U	U	U	U	U	U
Amyl Acetate	U	U	L	U	U	-	Butyl Alchol	L	U	E	G	E	G
Amyl Alchol	L	U	G	L	G	L	Butyl Cellosolve	U	U	E	G	-	-
Amyl Chlonde	U	U	U	U	U	-	Butyl Phenol	L	U	U	U	-	-
Aniline	U	U	U	U	U	U	Butylene	C	C	U	U	-	-
Aniline Chlorhydrat	U	U	U	U	U	U	Butyric Acid 20%	L	U	U	U	U	U

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC LLDPE EVA						Material Handled	PVC LLDPE EVA					
	Temperature (°C)							Temperature (°C)					
	20	65	20	65	20	65		20	65	20	65	20	65
Calcium Bisulfite	E	E	E	E	E	-	Copper Chloride	E	E	E	E	E	-
Calcium Carbonate	E	E	E	E	E	-	Copper Cyanide	E	E	E	E	E	-
Calcium Chlorate	E	E	E	E	E	-	Copper Fluoride 2%	E	E	E	E	E	-
Calcium Chloride	E	E	E	E	E	-	Copper Nitrate	E	G	E	G	E	-
Calcium Hydroxide	E	E	E	E	E	-	Copper Sulfate	E	G	E	E	E	-
Calcium Hypochlorite	E	E	G	E	G	-	Corn Oils	E	G	L	U	-	-
Calcium Nitrate	E	E	E	E	E	-	Cottonseed Oil	G	L	E	G	E	-
Calcium Sulfate	E	E	E	E	E	-	Creosote	U	U	U	U	U	U
Cane Sugar Liquors	E	E	G	G	G	-	Cresol	U	U	U	U	U	U
Carbon Bisulfide	U	U	U	U	U	U	Cresylic Acid 50%	U	U	U	U	U	U
Carbon Dioxide (Aqueous Solution)	E	E	E	E	E	-	Crude Oil	L	U	U	U	U	U
Carbon Dioxide Gas (Wet)	E	E	G	G	G	-	Cyclohexane	U	U	G	G	L	U
Carbon Monoxide	E	E	G	G	G	-	Cyclohexanol	U	U	G	L	E	L
Carbon Tetrachloride	U	U	L	U	U	U	Cyclohexanone	U	U	G	L	E	L
Carbonic Acid	L	U	G	G	G	G	Demineralized Water	E	E	E	E	E	E
Casein	E	L	E	E	E	-	Dextrin	E	E	E	E	E	-
Castor Oil	E	E	L	U	L	U	Dextrose	E	G	E	E	E	-
Caustic Potash	E	E	L	L	L	-	Di-acetone Alcohol	-	-	E	G	-	-
Caustic Soda	E	E	L	L	G	-	Dichlorobenzene	U	U	L	U	U	U
Cellosolve	L	U	G	L	L	U	Diesel Oils	L	U	-	-	-	-
Chloracetic Acid	E	U	G	L	U	U	Diethyl Ether	U	U	G	L	U	U
Chloral Hydrate	E	E	U	U	L	U	Diethylene Glycol	G	L	E	G	G	L
Chloric Acid 20%	E	E	-	-	-	-	Diglycolic Acid	E	G	E	G	E	-
Chlorinated Hydrocarbons	U	U	U	U	U	U	Di-isodecyl Phthalate	U	U	-	-	-	-
Chlorine Gas (Dry)	G	G	U	U	U	U	Dimethylamine	U	U	U	U	U	U
Chlorine Gas (Moist)	L	U	U	U	U	U	Diethyl Phthalate	U	U	G	L	G	U
Chlorine Water 2%	G	L	G	L	G	L	Disodium Phosphate	E	E	E	E	E	-
Chlorine Water Saturated	L	U	E	G	E	L	Distilled Water	E	E	E	E	E	E
Chlorobenzene	U	U	U	U	U	U	Ethers	U	U	G	L	U	U
Chloroform	U	U	L	U	U	U	Ethyl Acetate	U	U	E	G	L	U
Chlorsulfonic Acid	L	U	U	U	U	U	Ethyl Acrylate	U	U	-	-	-	-
Chrome Alum	E	E	E	G	E	G	Ethyl Alcohol 0 - 50%	G	L	E	E	G	L
Chromic Acid 10%	G	L	G	L	G	-	Ethyl Alcohol 50-98%	L	U	E	G	L	U
Chromic Acid 25%	G	L	G	L	G	-	Ethyl Chloride	U	U	U	U	U	U
Chromic Acid 30%	L	U	L	U	L	U	Ethyl Ether	U	U	U	U	U	U
Chromic Acid 40%	L	U	L	U	L	U	Ethylene Bromide	E	U	U	U	U	U
Chromic Acid 50%	L	U	L	U	L	U	Ethylene Dichloride	U	U	U	U	U	U
Chromic Acid Plating Solution	-	-	-	-	E	E	Ethylene Glycol	E	E	E	G	E	G
Cider	E	L	E	G	E	L	Ethylene Oxide	U	U	U	U	U	U
Citric Acid	E	E	E	E	E	E	Fatty Acids	E	E	G	L	L	U
Coal Tar	U	U	U	U	U	U	Ferric Chloride	E	E	E	E	E	-
Coconut Oil	G	L	G	L	L	U	Ferric Nitrate	E	E	E	E	E	-
							Ferric Sulfate	E	E	E	E	E	-
							Ferrous Chloride	E	E	E	E	E	-

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC LLDPE EVA						Material Handled	PVC LLDPE EVA					
	Temperature (°C)							Temperature (°C)					
Ferrous Sulfate	20	65	20	65	20	65	Hydrogen Cyanide	20	65	20	65	20	65
Fish Solubles	E	E	E	E	E	-	Hydrog. Peroxide 3-12%	C	C	C	C	C	C
Fluorine Gas - Dry	U	U	U	U	U	U	Hydrogen Peroxide 30%	E	G	G	L	G	L
Fluorine Gas - Wet	U	U	U	U	U	U	Hydrogen Peroxide 50%	E	L	L	U	U	U
Fluoroboric Acid	E	E	E	G	E	-	Hydrogen Peroxide 90%	U	U	U	U	U	U
Fluorosilicic Acid	E	E	G	L	G	-	Hydrogen Phosphide	E	L	G	G	E	E
Formic Acid	E	L	E	G	E	E	Hydrogen Sulfide (Aqueous Solution)	E	E	E	G	E	-
Formaldehyde (40% Aqueous)	U	U	G	L	E	G	Hydrogen Sulfide - Dry	E	E	E	G	E	-
Formic Acid 3%	-	-	-	-	E	E	Hydrom bromic Acid 20%	E	G	G	G	G	-
Formic Acid 10%	-	-	-	-	E	E	Hydroquinone	E	E	E	E	E	-
Formic Acid 25%	-	-	-	-	E	E	Hypochlorous Acid	E	E	E	G	L	U
Formic Acid 50%	-	-	-	-	E	E	Inks	-	-	E	E	E	E
Formic Acid 100%	-	-	-	-	U	U	Iodine (In Alcohol)	U	U	U	U	U	U
Freon - 12	L	U	G	L	G	-	Iso-octane	L	U	-	-	-	-
Fructose	E	E	E	E	E	-	Isopropyl Acetate	U	U	-	-	-	-
Fruit Pulps & Juices	E	E	E	E	E	-	Isopropylalcohol	E	G	E	E	E	-
Fuel Oil	G	L	G	U	U	U	Jelly	E	E	-	-	-	-
Furfural	U	U	U	U	U	U	Jet Fuels JP 3,4,5	U	U	-	-	-	-
Furfuryl Alcohol	-	-	-	-	U	U	Kerosene	U	U	L	U	U	U
Gallic Acid	E	E	E	E	E	-	Ketones	U	U	E	G	L	U
Gas - Natural (Dry)	C	C	U	U	U	U	Lacquer Thinners	U	U	E	G	L	U
Gas - Natural (Wet)	C	C	U	U	U	U	Lactic Acid 28%	E	E	E	E	E	-
Gelatine	E	E	E	E	E	-	Lard Oil	E	G	G	L	G	L
Glucose	E	E	E	E	E	-	Lauric Acid	E	E	L	U	-	-
Glycerine (Glycerol)	E	E	E	E	E	-	Lauryl Chloride	E	E	L	U	L	-
Glycol	E	E	E	E	E	-	Lauryl Sulfate	E	E	U	U	U	U
Glycolic Acid 30%	E	E	E	E	E	-	Lead Acetate	E	E	E	E	E	-
Grease	E	L	-	-	-	-	Lead Arsenate	E	E	-	-	E	E
Heptane	L	U	U	U	U	U	Lead Nitrate	E	E	-	-	E	E
Hexadecanol	-	-	-	U	U	U	Lead Tetra-ethyl	E	E	-	-	E	E
Hexane	L	U	E	E	-	-	Lemon Juice	E	G	-	-	-	-
Hexanol, Tertiary	L	U	G	L	L	U	Lime Sulfur	E	E	G	G	G	-
Hydrobromic Acid 20%	E	G	G	G	G	-	Linoleic Acid	E	E	-	-	-	-
Hydrochloric Acid 10%	E	G	E	E	E	E	Linseed Oil	E	E	L	U	L	U
Hydrochloric Acid 48%	E	G	E	G	G	-	Liquors (Chemical)	E	G	E	G	E	G
Hydrofluoric Acid 4%	G	G	G	G	E	E	Lubricating Oils	G	L	U	U	U	U
Hydrofluoric Acid 10%	G	L	G	G	E	E	Magnesium Carbonate	E	E	E	E	E	-
Hydrofluoric Acid 48%	G	U	G	L	E	E	Magnesium Chloride	E	E	E	E	E	-
Hydrofluoric Acid 60%	G	U	G	L	E	E	Magnesium Hyrdroxide	E	E	E	E	E	-
Hydrofluorosilicic Acid	G	L	-	-	-	-	Magnesium Nitrate	E	E	E	E	E	-
Hydrogen	C	C	C	C	C	C	Magnesium Sulfate	E	E	E	E	E	-
Hydrogen Bromide (Dry)					E	E	Maleic Acid 25% Aqueous	E	E	G	G	E	E
Hydrogen Chloride (Dry)					E	E	Maleic Acid 50%	-	-	E	E	E	E

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC	LLDPE	EVA	Material Handled						PVC	LLDPE	EVA		Material Handled					
	Temperature (°C)						Temperature (°C)												
	20	65	20	65	20	65		20	65	20	65	20	65		20	65	20	65	
Maleic Acid Concentrated	-	-	E	G	E	G	Orange Juice	E	E	G	L	-	-						
Malic Acid	E	E	G	G	G	-	Oxalic Acid	E	G	E	G	G	G						
Mayonnaise	E	E	-	-	-	-	Oxygen	E	G	G	L	G	L						
Mercuric Chloride	G	L	G	G	G	G	Ozone	L	U	L	U	U	U						
Mercuric Cyanide	U	U	G	G	G	G	Palmitic Acid 10%	E	E	G	L	E	G						
Mercurous Nitrate	G	G	G	G	G	-	Palmitic Acid 70%	L	U	G	U	L	U						
Mercury	G	G	G	G	G	L	Paraffin	E	G	G	L	L	U						
Methyl Acetate	U	U	-	-	U	U	Pentane	L	U	-	-	-	-						
Methyl Alcohol	L	U	E	G	E		Peracetic Acid 40%	U	U	-	-	-	-						
Methyl Bromide	U	U	-	-	U	U	Perchlorethylene	U	U	-	-	-	-						
Methyl Chloride	U	U	U	U	U	U	Perchloric Acid 10%	G	L	G	G	G	G						
Methyl Ethyl Ketone	U	U	E	G	L	U	Perchloric Acid 70%	L	U	G	L	G	-						
Methyl Isobutyl Ketone	U	U	E	G	L	U	Petrol	U	U	-	-	U	U						
Methyl Sulfate	E	G	-	-	-	-	Petroleum Ether	L	L	-	-	U	U						
Methyl Sulfuric Acid	E	E	G	G	E	E	Phenol	U	U	U	U	U	U						
Methylated Spirit	-	-	-	-	E	G	Phenylhydrazine	U	U	L	U	-	-						
Methylene Chloride	U	U	U	U	U	U	Phenylhydrazine												
Milk	E	E	E	E	G	L	Hydrochloride	L	U	L	U	-	-						
Mineral Oils	G	L	L	U	L	U	Phosgene (Gas)	C	C	-	-	C	U						
Mineral Spirits	-	-	E	G	-	-	Phosgene (Liquid)	U	U	-	-	-	-						
Molasses	E	E	E	E	E	-	Phosphoric Acid 0-25%	E	G	E	G	E	G						
Monochlorobenzene	U	U	-	-	-	-	Phosphoric Acid 25-50%	E	G	E	G	E	G						
Naphtha	U	U	G	L	U	U	Phosphoric Acid 50-90%	E	G	G	L	E	L						
Naphthalene	U	U	L	U	U	U	Phosphorus (Yellow)	G	L	L	L	U	U						
Nickel Acetate	E	E	E	E	E	-	Phosphorus Pentoxide	L	U	G	L	G	L						
Nickel Chloride	E	E	E	E	E	-	Phosphorus Trichloride	U	U	L	U	L	U						
Nickel Nitrate	E	E	E	E	E	-	Photographic Developers	L	U	E	E	E	E						
Nickel Sulphate	E	E	E	E	E	-	Photographic Emulsions	L	U	E	E	E	E						
Nicotine	E	E	E	E	E	-	Photographic Fixers	L	U	E	E	E	E						
Nicotine Acid	E	G	E	E	E	-	Picric Acid	U	U	G	U	G	L						
Nitric Acid (Anhydrous)	U	U	U	U	U	U	Pitch	G	L	E	G	-	-						
Nitric Acid 10%	E	G	G	G	G	G	Plating Solutions												
Nitric Acid 25%	G	L	G	G	G	L	Brass	E	E	G	G	L	-						
Nitric Acid 35%	G	L	G	U	L	U	Cadmium	E	E	G	G	L	-						
Nitric Acid 40%	G	L	L	U	L	U	Chromium	G	G	U	U	U	U						
Nitric Acid 50%	G	U	L	U	L	U	Copper	E	E	G	G	L	-						
Nitric Acid 60%	G	U	L	U	U	U	Gold	E	E	G	G	L	-						
Nitric Acid 68%	L	U	U	U	U	U	Jodium	E	E	G	G	L	-						
Nitric Acid 70%	U	U	U	U	U	U	Lead	E	E	G	G	L	-						
Nitrobenzene	U	U	U	U	U	U	Nickel	E	E	G	G	L	-						
Nitrous Oxide	E	E	-	-	-	-	Rhodium	E	E	G	G	L	-						
Oils & Fats	E	G	G	L	G	U	Silver	E	E	G	G	L	-						
Oils, Petroleum	E	G	G	L	G	U	Tin	E	E	G	G	L	-						
Oleic Acid	G	L	L	U	U	U	Zinc	E	G	G	G	L	-						
Oleum	U	U	U	U	U	U	Potable Water	E	G	E	E	E	G						

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC	LLDPE	EVA	Temperature (°C)						Material Handled	PVC	LLDPE	EVA	Temperature (°C)													
	20	65	20	65	20	65		20	65	20	65	20	65		20	65	20	65	20	65							
Potassium Acid Sulfate	E	E	E	G	G	-	Silver Cyanide	E	E	E	E	E	-	Silver Nitrate	E	E	E	E	E	-							
Potassium Antimonate	E	E	E	E	E	-	Silver Plating Solutions	E	G	E	G	E	-	Soap Solution	E	G	G	L	G	L							
Potassium Bicarbonate	E	E	E	E	E	-	Sodium Acetate	E	E	E	E	E	-	Potassium Bisulfite	E	E	E	E	E	-							
Potassium Bichromate	E	E	E	E	E	-	Potassium Bisulphate	G	L	E	E	E	-	Potassium Borate 1%	E	E	E	E	E	-							
Potassium Bromate 10%	E	E	E	G	E	-	Sodium Arsenite	E	E	E	E	E	-	Potassium Bromide	E	E	G	E	E	-							
Potassium Carbonate	E	E	E	E	E	-	Sodium Benzoate	E	G	E	E	E	-	Potassium Chlorate	E	E	E	E	E	-							
Potassium Chloride	E	E	E	E	E	-	Sodium Bisulfate	E	E	E	E	E	-	Potassium Chromate 40%	E	E	E	E	E	-							
Potassium Cuprocyanide	E	E	E	E	E	-	Sodium Bisulfite	E	E	E	E	E	-	Potassium Cyanide	C	C	C	C	C	C	Sodium Bromide	E	E	E	E	E	-
Potassium Dichromate 40%	E	E	E	E	E	-	Sodium Carbonate	E	E	E	E	E	-	Potassium Dichromate 40%	E	E	E	E	E	-							
Potassium Ferricyanide	E	E	E	E	E	-	Sodium Chlorate	G	L	E	E	E	-	Potassium Fluoride	E	E	E	E	E	-							
Potassium Fluoride	E	E	E	E	E	-	Sodium Chloride	E	E	E	E	E	-	Potassium Hydroxide 10%	E	E	E	E	E	-							
Potassium Hydroxide 10%	E	E	E	E	E	-	Sodium Cyanide	E	E	E	E	E	-	Potassium Hydroxide 20%	E	E	E	E	E	-							
Potassium Hydroxide 20%	E	E	E	E	E	-	Sodium Dichromate	E	G	E	E	E	-	Potassium Hydroxide 35%	E	E	E	E	E	-							
Potassium Hydroxide 35%	E	E	E	G	G	-	Sodium Ferricyanide	E	E	E	E	E	-	Potassium Hydroxide Conc	-	-	-	E	L	Sodium Fluoride	E	E	E	E	E	-	
Potassium Hypochlorite	G	L	G	L	E	-	Sodium Hydroxide 10%	E	E	E	E	E	-	Potassium Nitrate	E	E	G	G	E	Sodium Hydroxide 35%	E	G	E	E	E	-	
Potassium Nitrate	E	E	G	G	E	E	Sodium Hydroxide 50%	G	L	-	-	-	-	Potassium Perborate	E	E	G	L	E	E	Sodium Ferrocyanide	E	E	E	E	E	-
Potassium Perchlorite	E	E	G	G	G	-	Sodium Hypochlorite	E	E	E	E	E	-	Potassium Permanganate 10%	G	G	E	E	E	Sodium Fluoride	E	E	E	E	E	-	
Potassium Permanganate 10%	G	G	E	E	U	U	Sodium Nitrate	E	E	E	E	E	-	Potassium Persulfate	E	E	E	E	E	Sodium Hydroxide 10%	E	E	E	E	E	-	
Potassium Persulfate	E	E	E	E	E	-	Sodium Nitrite	E	E	E	E	E	-	Potassium Phosphate	-	-	-	E	E	Sodium Hydroxide 35%	E	G	E	E	E	-	
Potassium Phosphate	-	-	-	-	E	E	Sodium Phosphate - Acid	G	G	E	E	E	-	Potassium Sulfate	E	E	E	E	E	Sodium Silicate	E	E	E	E	E	-	
Potassium Sulfate	E	E	E	E	E	-	Sodium Sulfate	E	E	E	E	E	-	Potassium Sulfide	E	E	E	E	E	Sodium Sulfide	E	E	E	E	E	-	
Potassium Sulfide	E	E	E	E	E	-	Sodium Sulfite	E	E	E	E	E	-	Potassium Thiosulfate	E	E	E	E	E	Sodium Sulfite	E	E	E	E	E	-	
Potassium Thiosulfate	E	E	E	E	E	-	Sodium Thisulfate (Hypo)	E	E	E	E	E	-	Power Steering Fluid	E	L	-	-	-	Sodium Sulfite	E	E	E	E	E	-	
Power Steering Fluid	E	L	-	-	-	-	Soft Drinks	E	G	E	E	G	L	Propane	C	C	U	U	U	U	Sodium Sulfate	E	E	E	E	E	-
Propargyl Alcohol	E	E	U	U	U	U	Soya Oil	E	G	-	-	-	-	Propyl Alcohol	E	L	E	E	E	E	Soybean Oil	G	L	-	-	-	-
Propyl Alcohol	E	L	E	E	E	-	Stannic Chloride	E	E	E	E	E	-	Propylene Dichloride	U	U	U	U	U	U	Stannous Chloride	E	G	E	E	E	-
Propylene Dichloride	U	U	U	U	U	U	Starch	-	-	-	-	E	E	Propylene Glycol	-	-	-	E	E	E	Stannous Chloride	E	G	E	E	E	-
Propylene Glycol	-	-	-	-	E	E	Stearic Acid	L	L	E	E	E	-	Salicylic Acid	-	-	-	E	E	E	Starch	-	-	-	E	E	-
Salicylic Acid	-	-	-	-	E	E	Stoddard Solvent	L	U	G	L	L	U	Salt Water	E	E	E	E	E	E	Soybean Oil	G	L	-	-	-	-
Salt Water	E	E	E	E	E	E	Styrene	U	U	-	-	-	-	Selenic Acid	E	G	G	L	L	U	Stannic Chloride	E	E	E	E	E	-
Selenic Acid	E	G	G	L	G	L	Sucrose	-	-	-	-	E	E	Shortening	G	L	E	E	E	E	Stannous Chloride	E	G	E	E	E	-
Shortening	G	L	E	E	E	E	Sulfur	G	G	E	E	E	E	Silicic Acid	-	-	-	E	E	E	Starch	-	-	-	E	E	-
Silicic Acid	E	E	E	E	E	-	Sulfur	G	G	E	E	E	E	Silicone Fluids	-	-	-	E	E	E	Soybean Oil	G	L	-	-	-	-

Chemical Resistance Guide

Key: E=Excellent G=Good L=Limited U=Unsatisfactory C=Cautionary

Material Handled	PVC	LLDPE	EVA	Temperature (°C)						Material Handled	PVC	LLDPE	EVA	Temperature (°C)					
	20	65	20	65	20	65					20	65	20	65	20	65			
Sulfuric Acid 0 - 10%	E	G	E	G	G	-					E	E	E	E	E	-			
Sulfuric Acid 10 - 40%	E	G	G	G	G	G					E	E	E	E	E	-			
Sulfuric Acid 50 - 60%	E	G	G	L	G	L					E	E	E	E	E	-			
Sulfuric Acid 70%	E	G	L	U	L	U					E	E	E	E	E	-			
Sulfuric Acid 95%	U	U	U	U	U	U					E	E	-	-	-	-			
Sulfuric Acid 95% to Fumin	L	L	U	U	U	U					G	L	E	E	-	-			
Sulfurous Acid	E	E	G	L	L	U					U	U	G	L	U	U			
Sulphur Dioxide - Liquid	L	U	U	U	U	U					E	E	E	E	E	-			
Sulphur Dioxide Gas - Dry	E	E	G	G	E	G					E	E	E	E	E	-			
Sulphur Dioxide Gas - Wet	L	U	G	L	E	L					E	E	E	E	E	-			
Sulphur Trioxide	E	G	U	U	U	U					Zinc Nitrate	E	E	E	E	E	-		
Sulphurous Acid 10%	-	-	-	-	E	E					Zinc Sulfate	E	E	E	E	E	-		
Sulphurous Acid 30%	-	-	-	-	U	U													
Tallow	E	E	E	E	E	E													
Tannic Acid	E	E	E	E	E	E													
Tanning Extracts	-	-	-	-	E	E													
Tanning Liquors	E	E	G	L	L	-													
Tartaric Acid	E	E	E	E	E	-													
Tea (Brewed)	E	G	E	G	G	L													
Tetraethyl Lead	G	L	-	-	-	-													
Tetrahydrofurane	U	U	U	U	U	U													
Thionyl Chloride	U	U	U	U	U	U													
Tin Chloride	E	E	-	-	-	-													
Titanium Tertachloride	E	U	-	-	-	-													
Titanium Trichloride	-	-	-	-	U	U													
Toluol or Toluene	U	U	E	G	U	U													
Tomato Juice	E	E	G	L	L	U													
Transformer Oil					U	U													
Transmission Fluid	E	L																	
Tributyl Phosphate	U	U	-	-	-	-													
Trichlorobenzene	U	U	-	-	U	U													
Trichloroethylene	U	U	G	L	U	U													
Tricresyl Phosphate	U	U	L	L	U	U													
Triethanolamine	L	U	G	L	L	-													
Triethylamine	G	L	-	-	-	-													
Trimethyl Propane	L	U	-	-	-	-													
Trisodium Phosphate	E	E	E	E	E	-													
Turpentine	L	U	G	L	U	-													
Urea	E	E	E	E	E	-													
Varnish	E	E	E	E	E	-													
Varsol			E	G															
Vegetable Oils	G	L			U	U													
Vinegar	E	E	E	G	E														
Vinyl Acetate	U	U	L	U	U	U													
Vinyl Chloride	U	U																	